



Polyisobutylene TPC 1350
Sales Specification

COMPONENT	UNITS	MIN	MAX	TEST METHOD	COA
KINEMATIC VISCOSITY @ 100°C	cSt	4000	4500	ASTM D-445	*
FLASH POINT, CLEVELAND OPEN CUP	°C	210	-	ASTM D-92	*
SPECIFIC GRAVITY @ 15.6°C/15.6°C		.90	.94	ASTM D-4052	*
COLOR	APHA	-	50	ASTM D-1209	*
HAZE, PHOTOMETRIC	NTU	-	4	ASTM D-6181	*
APPEARANCE	CLEAR and BRIGHT				*