



**Polyisobutylene TPC 175**  
Sales Specification

<b>COMPONENT</b>	<b>UNITS</b>	<b>MIN</b>	<b>MAX</b>	<b>TEST METHOD</b>	<b>COA</b>
KINEMATIC VISCOSITY @ 100°C	cSt	75	95	ASTM D-445	*
FLASH POINT, CLEVELAND OPEN CUP	°C	140	-	ASTM D-92	*
SPECIFIC GRAVITY @ 15.6°C/15.6°C		.87	.90	ASTM D-4052	*
COLOR	APHA	-	70	ASTM D-1209	*
HAZE, PHOTOMETRIC	NTU	-	4	ASTM D-6181	*
APPEARANCE	CLEAR and BRIGHT				*