



Polyisobutylene TPC 5230
Sales Specification

COMPONENT	UNITS	MIN	MAX	TEST METHOD	COA
MOLECULAR WEIGHT	Mn	2100	2500	GPC1	*
POLDISPERSITY		Report	-	GPC1	*
KINEMATIC VISCOSITY @ 100°C	cSt	1400	1800	ASTM D-445	*
FLASHPOINT, CLEVELAND OPEN CUP	°C	210	-	ASTM D-92	*
SPECIFIC GRAVITY @ 15.6°C/15.6°C		.89	.93	ASTM D-4052	*
COLOR	APHA	-	50	ASTM D-1209	*
HAZE, PHOTOMETRIC	NTU	-	4	ASTM D-6181	*
ALPHA VINYLIDENE	%	80	-	GC	*
APPEARANCE	CLEAR and BRIGHT				*