



Polyisobutylene TPC 575
Sales Specification

COMPONENT	UNITS	MIN	MAX	TEST METHOD	COA
MOLECULAR WEIGHT	Mn	700	800	GPC2	*
POLYDISPERSITY		-	1.8	GPC2	*
KINEMATIC VISCOSITY @ 100°C	cSt	65	95	ASTM D-445	*
FLASH POINT, CLEVELAND OPEN CUP	°C	160	-	ASTM D-92	*
SPECIFIC GRAVITY @ 15.6°C/15.6°C		.87	.89	ASTM D-4052	*
COLOR	APHA	-	70	ASTM D-1209	*
HAZE, PHOTOMETRIC	NTU	-	4	ASTM D-6181	*
ALPHA VINYLIDENE	%	80	-	GC	*
APPEARANCE	CLEAR and BRIGHT				*